

LISTING OF THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. **(Currently Amended)** A pigment paste composition comprising:
about 15-30% by weight of pigment grinding vehicle, wherein said pigment grinding vehicle is obtainable from about 25-35% by weight of polyglycidyl ether of bisphenol A having an epoxy equivalence in a range of about 900-1200, about 5-12% by weight of ~~propyleneglicol~~ propyleneglycol monomethyl ether acetate, about 8-15% by weight of partially blocked isocyanate cross-linking agent, about 25-40% by weight of ethylene glycol monobutyl ether, about 10-20% by weight of organic tertiary amino acid salt and about 0-5% by weight of deionized water;
about 2-6% by weight of an anticorrosive pigment; and
about 0.7-2.3% by weight of dibutyl tin oxide,
a ratio of solid content of said pigment/pigment grinding vehicle being about 1/0.2-1/0.45.

2. **(Currently Amended)** ~~[[A]] The pigment paste composition comprising:~~
~~about 15-30% by weight of pigment grinding vehicle;~~
~~about 2-6% by weight of an anticorrosive pigment; of claim 1,~~ wherein the anticorrosive pigment is anyone selected from the group consisting of bismuth hydroxide, bismuth trioxide, bismuth oxide, aluminum tri-polyphosphate hydrate and magnesium aluminum hydroxide carbonate hydrate;~~and~~
~~about 0.7-2.3% by weight of dibutyl tin oxide;~~
~~a ratio of solid content of said pigment/pigment grinding vehicle being about 1/0.2-1/0.45.~~